

ATLAS 96® HD

Vinyl Vapor Retarder Film Product Data Sheet

TECHNICAL INFORMATION

<u>Properties</u>	<u>Values</u>	<u>Test Method</u>
Thickness	3.2 mil ± 10%	ASTM-D-1593
Yield	39.0 sq. ft./lb. ± 5%	Determined by wt
Cold Temp. Installation	+7°F	
Tensile Strength	M.D. 3250 psi T.D. 2750 psi	ASTM-D-882
Elongation	M.D. 180% T.D. 190%	ASTM-D-882
Tear Strength	M.D. 185 grams T.D. 385 grams	ASTM-D-1922
Dimensional Stability	M.D. -4.0% T.D. +0.5%	ASTM 1204
Permeance, Perms	1.0	ASTM-E-96
U.L. Fire Hazard Classification: (Composite)		
Flame Spread	25	U.L. 723
Smoke Developed	50	(ASTM-E-84 Tunnel)
Width	As ordered ± ¼	Tape

We believe all information given is accurate. It is offered in good faith, but without guarantee. Since conditions of use are beyond our control, all risks of use are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.

7/1/2004

atlashd/ch